

## PRODUCT IDENTIFICATION SHEET

<b>Product Trade Name</b>	<b>Magic<sup>®</sup> II Composite Blast Media (Type VIII)</b>
<b>Product Description</b>	A Nanostructured composite abrasive media made from blended amino thermoset resins, reinforcing fiber, and acrylate polymer, polymerized and cross-linked
<b>Size</b>	30/60 Mesh – U.S. Standard Sieve* 20/40 Mesh – U.S. Standard Sieve*
<b>Hardness</b>	54-60 Barcol
<b>Density</b>	1.36 to 1.46
<b>Strip Rate</b>	@20 psi 1.00 sq. ft./minute 1/2" or 3/8" Double venturi nozzle Mil Spec epoxy primer & urethane topcoat
<b>Consumption</b>	@25 psi 6% per cycle Mil Spec test method
<b>Conductivity*</b>	100.00 $\mu^s$ maximum
<b>Heavy Particulates*</b>	0.02 maximum
<b>Light Particulates*</b>	1.00 maximum
<b>Anti-static Level*</b>	1" minimum
<b>Specific Gravity</b>	1.36 to 1.46
<b>Ash</b>	2.00% maximum
<b>Extract</b>	95% minimum
<b>pH</b>	8 maximum

\*Mil Spec Mil P85891 test protocol.